

Certificate of Analysis

300 Technology Drive Christiansburg, VA 24073 USA inorganicventures.com P: 800-669-6799/540-585-3030 F: 540-585-3012 info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).



2.0 PRODUCT DESCRIPTION

Product Code: Single Analyte Mass Spec Solution

Catalog Number: MSU-100PPM

Lot Number: U2-U736347

Matrix: 1% (v/v) HNO3

Value / Analyte(s): 100 μg/mL ea:

Uranium

Starting Material: Uranyl Nitrate Hexahydrate

Starting Material Lot#: 2504

Starting Material Purity: 99.9993%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: $99.82 \pm 0.66 \mu g/mL$

Density: 1.004 g/mL (measured at 20 ± 4 °C)

Assay Information:

 ANALYTE
 METHOD
 NIST SRM#
 SRM LOT#

 U
 ICP Assay
 traceable to 3164
 R2-U689597

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, X_{CRM/RM}, where two or more methods of characterization are

used is the weighted mean of the results:

 $X_{CRM/RM} = \Sigma(w_i) (X_i)$

X_i = mean of Assay Method i with standard uncertainty u_{char i}

 $\mathbf{w_i}$ = the weighting factors for each method calculated using the inverse square of

the variance:

 $\mathbf{w_i} = (1/\mathsf{u_{char\;i}})^2 \, / \, (\Sigma (1/(\mathsf{u_{char\;i}})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k (u_{char}^2 + u_{bb}^2 + u_{lts}^2 + u_{ts}^2)^{\frac{1}{2}}$

k = coverage factor = 2

 $\mathbf{u_{char}} = [\Sigma((\mathbf{w_i})^2 (\mathbf{u_{char}}_i)^2)]^{\frac{1}{2}}$ where $\mathbf{u_{char}}_i$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

 $\mathbf{u_{lts}}$ = long term stability standard uncertainty (storage)

uts = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, X_{CRM/RM}, where one method of characterization is used is the mean of individual results:

 $X_{CRM/RM} = (X_a) (u_{char a})$

X_a = mean of Assay Method A with

u_{char a} = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k (u_{char}^2 + u_{bb}^2 + u_{lts}^2 + u_{ts}^2)^{1/2}$

k = coverage factor = 2

 $u_{char\ a}$ = the errors from characterization

 $u_{
m bb}$ = bottle to bottle homogeneity standard uncertainty $u_{
m lts}$ = long term stability standard uncertainty (storage)

uts = transport stability standard uncertainty

IV's Certified Abundance

Isotope	Atom %
Uranium 238U	99.8 ± 0.1
Uranium 235U	0.19 ± 0.05

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to $0.3 \, \mu m$.

М	Ag	<	0.001400	М	Eu	<	0.000270	М	Na		0.000181	М	Se	<	0.004800	М	Zn		0.000213
M	ΑI		0.000032	М	Fe		0.000750	M	Nb	<	0.000790	i	Si	<		М	Zr	<	0.000270
M	As	<	0.007300	М	Ga	<	0.000270	M	Nd	<	0.000270	M	Sm	<	0.000270				
M	Au	<	0.001400	М	Gd	<	0.000270	М	Ni		0.000090	M	Sn	<	0.120000				
M	В	<	0.017000	М	Ge	<	0.000800	М	Os	<	0.000270	M	Sr	<	0.000270				
М	Ва	<	0.003100	М	Hf	<	0.000270	i	Р	<		М	Та	<	0.000270				
М	Ве	<	0.003200	М	Hg	<	0.000270	М	Pb		0.000051	М	Tb	<	0.000270				
М	Bi	<	0.003000	М	Но	<	0.000270	М	Pd	<	0.000270	М	Те	<	0.001100				
M	Ca	<	0.048000	М	ln	<	0.001400	М	Pr	<	0.000270	M	Th		0.000020				
М	Cd	<	0.000270	М	lr	<	0.000270	М	Pt	<	0.000270	М	Ti	<	0.000530				
М	Ce	<	0.000270	0	K	<	0.047000	М	Rb	<	0.000660	М	TI	<	0.000270				
М	Co	<	0.000270	М	La		0.000032	М	Re	<	0.000270	М	Tm	<	0.000270				
М	Cr		0.000173	М	Li	<	0.001100	М	Rh	<	0.000270	s	U	<					
М	Cs	<	0.003500	М	Lu	<	0.000270	М	Ru	<	0.000270	М	V	<	0.003500				
M	Cu	<	0.005600	М	Mg		0.000024	i	S	<		M	W	<	0.000270				
M	Dy	<	0.000270	М	Mn	<	0.006500	М	Sb	<	0.000270	M	Υ	<	0.000270				
M	Er	<	0.000270	М	Мо		0.000043	М	Sc	<	0.000800	М	Yb	<	0.000270				

M - Checked by ICP-MS

O - Checked by ICP-OES

i - Spectral Interference

n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

- **6.1** This standard is intended for the calibration of analytical instruments and validation of analytical methods as appropriate. This CRM may be used in connection with EPA Methods 6010, 6020 (all versions), Standard Methods 3120 B and USP <232> / ICH Q3D.
- **6.2** For products attaining traceability through Inorganic Ventures' Primary Certified Reference Materials (PCRM™) see the Limited License to Use PCRM™ in the Inorganic Ventures <u>Terms and Conditions of Sale</u>, https://www.inorganicventures.com/terms-and-conditions-sale. The Terms and Conditions contain information on the use of materials traceable to PCRM™ certified reference materials. This Limited License agreement is especially pertinent for laboratories accredited under ISO:17034.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° 30° C while in sealed TCT bag.
- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.
- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° 24° C to minimize the effects of transpiration. Use at $20^{\circ} \pm 4^{\circ}$ C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.
- For more information, visit www.inorganicventures.com/TCT

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 238.03 +6 8 UO22+(uranyl) Chemical Compatibility - Soluble in HCl and HNO3. Avoid H3PO4. H2SO4 and HF matrices should not be a problem depending upon [U]. Although the UO22+ ion is distinctly basic, any U+4 will precipitate in basic media. UO22+salts are generally soluble in water and UO22+ is stable with most metals and inorganic anions. The uranyl phosphate is insoluble in water. UF4 and UF6 are water soluble.

Stability - 2-100 ppb levels stable for months in 1% HNO3 / LDPE container. 1-10,000 ppm solutions chemically stable for years in 2-5% HNO3 / LDPE container.

U Containing Samples (Preparation and Solution) -Metal (Dissolves rapidly in HCl and HNO3); Oxide (Soluble in HNO3); Ores (Digest for 1-2 hours with 1 gram of ore to 30 mL 1:1 HNO3. Silica insolubles are removed by filtration after bringing the sample to fumes with conc. H2SO4.)

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	Estimated D.L.	Order	Interferences (underlined indicates severe)
ICP-MS 238 amu	2 ppt	N/A	206Pb16O2
ICP-OES 263.553 nm	0.3 / 0.01 μg/mL	1	Ce, Ir, Th, Rh, W, Zr,
			Ta, Ti, V, Hf, Fe, Re,
			Ru
ICP-OES 367.007 nm	0.3 / 0.02 μg/mL	1	Th, Ce
ICP-OES 385.958 nm	0.3 / 0.01 μg/mL	1	Th, Fe

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

September 13, 2023

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- September 13, 2028
- The date after which this CRM/RM should not be used.
- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

Sealed TCT Bag Or	oen Date:	
oculou for bug of	on Date.	

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS Certificate Prepared By:

Uyen Truong
Custom Processing Supervisor

Certificate Approved By:

Muzzammil Khan Stock Laboratory Supervisor

Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director

Mayyan Ph Paul R. Saines